

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**




## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : <b>A61L 29/00</b>	<b>A1</b>	(11) International Publication Number: <b>WO 95/23619</b>
		(43) International Publication Date: 8 September 1995 (08.09.95)
<p>(21) International Application Number: PCT/US95/02717</p> <p>(22) International Filing Date: 2 March 1995 (02.03.95)</p> <p>(30) Priority Data: 08/204,554 2 March 1994 (02.03.94) US</p> <p>(71) Applicant: SCIMED LIFE SYSTEMS, INC. [US/US]; One Scimed Place, Maple Grove, MN 55311-1566 (US).</p> <p>(72) Inventors: WANG, Lixiao; 12811 - 86th Place North, Maple Grove, MN 55369 (US). CHEN, Jianhua; Apartment #207, 6400 67th Avenue North, Brooklyn Park, MN 55428 (US).</p> <p>(74) Agents: STEINKRAUS, Walter, J. et al.; Suite 1540, 920 Second Avenue South, Minneapolis, MN 55402-4014 (US).</p>		<p>(81) Designated States: CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p><b>Published</b> With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</p>

(54) Title: BLOCK COPOLYMER ELASTOMER CATHETER BALLOONS

## (57) Abstract

Balloons for medical devices, particularly balloon angioplasty catheters, are made from particular block copolymer thermoplastic elastomers in which the block copolymer is made up of hard segments of a polyester or polyamide and soft segments of polyether; the polyester hard segments are polyesters of an aromatic dicarboxylic acid and a C<sub>2</sub>-C<sub>4</sub> diol; the polyamide hard segments are polyamides of C<sub>6</sub> or higher carboxylic acids and C<sub>6</sub> or higher organic diamines or of C<sub>6</sub> or higher aliphatic ω-amino-α-acids, and the polyether soft segments are polyethers of C<sub>2</sub>-C<sub>10</sub> diols; the block copolymer has a low flexural modulus, namely less than 150,000 psi; the block copolymer has a hardness, Shore D scale, of greater than 60; and the percentage by weight of the block polymer attributable to the hard segments is between about 50 % and about 95 %. The polymers provide high strength, thin wall, compliant and semi-compliant balloons, which leads to a low profile catheter. The low profile catheters have very good initial crossing, good trackability, good recrossing after first inflation.



**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

## BLOCK COPOLYMER ELASTOMER CATHETER BALLOONS

5

### Background of the Invention

Balloons mounted on the distal ends of catheters are widely used in medical treatment. The balloon may be used to widen a vessel into which the catheter is inserted or to force open a blocked vessel. The requirements for strength and size of the balloons vary widely depending on the balloon's intended use and the vessel size into which the catheter is inserted. Perhaps the most demanding applications for such balloons are in balloon angioplasty in which catheters are inserted for long distances into extremely small vessels and used to open stenoses of blood vessels by balloon inflation. These applications require extremely thin walled high strength relatively inelastic balloons of predictable inflation properties. Thin walls are necessary because the balloon's wall and waist thicknesses limit the minimum diameter of the distal end of the catheter and therefore determine the limits on vessel size treatable by the method and the ease of passage of the catheter through the vascular system. High strength is necessary because the balloon is used to push open a stenosis and so the thin wall must not burst under the high internal pressures necessary to accomplish this task. The balloon must have some elasticity so that the inflated diameter can be controlled, so as to allow the surgeon to vary the balloon's diameter as required to treat individual lesions, but that elasticity must be relatively low so that the diameter is easily controllable. Small variations in pressure must not cause wide variation in diameter.

While angioplasty balloons are considered inelastic relative to balloons used in most other applications, there is in the art a general classification of such balloons based on their expandability or "compliance" relative to each other. As used herein, "non-compliant" balloons are the least elastic, increasing in diameter about 2-7%, typically about 5%, as the balloon is pressurized from an inflation pressure of about 6 atm to a pressure of about 12 atm, that is, they have a "distension" over that pressure range of about 5%. "Semi-compliant" balloons have somewhat greater distensions,

generally 7-16% and typically 10-12% over the same pressurization range. "Compliant" balloons are still more distensible, having distensions generally in the range of 16-40% and typically about 21% over the same pressure range. Maximum distensions, *i.e.* distension from nominal diameter to burst, of various balloon materials may be

5 significantly higher than the distension percentages discussed above because wall strengths, and thus burst pressures, vary widely between balloon materials. The 6-12 atm inflation range is used in the present application to allow direct comparison of the compliance attributes of various balloons.

The strength of the polymer materials used in the balloons varies widely.

10 The strongest balloons are also the most inelastic, being made of highly orientable polymers such as polypropylene, polyethylene terephthalate or other phthalate polyesters or copolyesters, and nylons. Tensile wall strengths are commonly 20,000-50,000 psi. Commercial angioplasty balloons made of such materials with nominal diameters in the range of 1.5-4.5 mm have distensions in the non-compliant to semi-

15 compliant range and can often be rated to pressures of 16 atm or higher without risk of bursting (actual burst pressures may exceed 20 atm). Generally, however, as compliance increases the wall strength decreases. Other semi-compliant and compliant balloons are made of less highly orientable polymers such as ethylene-vinyl acetate, polyvinyl chloride, olefin copolymers and ionomer resins. The wall strengths of

20 balloons made from these less orientable materials are still lower than those made from the highly orientable polymers, commonly in the range of 6,000-15,000 psi, resulting in lower rated maximum inflation pressures of 9-10 atm.

The particular distension and maximum pressure attributes of a balloon are also influenced both by polymer type and by the conditions under which the balloon

25 is blown. Angioplasty balloons are conventionally made by blowing a tube of polymer material at a temperature above its glass transition temperature. For any given balloon material, there will be a range of distensions achievable depending on the conditions chosen for the blowing of the balloon.

In US 4,906,244 to Pinchuck there are described balloons of nylon (*i.e.* aliphatic polyamide) materials, such as nylon 12, nylon 11, nylon 9, nylon 6/9 and nylon

30 6/6. Like all other polymer materials the distensions of these balloons can be determined, within a range, by controlling blowing conditions such as initial dimensions

of tubing, prestretching, hoop ratio and heat set conditions. The data in the reference show that compliance characteristics can be obtained ranging from non-compliant to semi-compliant characteristics and that wall strengths of greater than 15,000 can be obtained. The reference suggests that higher compliances can be achieved with nylon  
5 materials but there is no indication of what other nylons or other balloon forming conditions could be employed to do so.

It has also been suggested to prepare balloons of thermoplastic elastomers in US 4,254,774 to Boretos, and polyamide elastomers have been mentioned among a number of possible balloon materials suggested in US 5,250,069 to  
10 Nobuyoshi, et al, but there are many of such thermoplastic elastomer polymers and before the invention hereof it has been expected that performance of balloons made from these materials would not be generally any better than high to intermediate compliance made from conventional thermoplastic polymers such as polyethylene ionomer, polyvinyl chloride, polyethylene or ethylene-vinyl acetate.

15 In US 5,290,306 polyester ethers and polyetheresteramide polymers of Shore D hardness less than 55 have been proposed for use as a sleeve or co-extruded outer layer to a balloon of a biaxially oriented nylon or polyethylene terephthalate (PET) material, so as to provide the balloon with improved softness and pin-hole and abrasion resistance.

20 Polyurethane block copolymers having flexural modulus of about 190,000 and an ultimate elongation of 250% are disclosed as balloon materials in EP 0592885 and mention is made of also using polyester block copolymers or polyamide block copolymers but no suggestion is made that such alternative copolymers could be usefully employed if their flexural modulus was substantially lower or their ultimate  
25 elongation was substantially higher than the disclosed polyurethane block copolymers.

### Summary of the Invention

New balloon materials, which possess a unique combination of physical properties including non-compliant, semi-compliant and compliant distension attributes,  
30 good flexibility and high tensile strength, are made from particular block copolymer thermoplastic elastomers characterized as follows:

the block copolymer is made up of hard segments of a polyester or polyamide and soft segments of polyether;

the polyester hard segments are polyesters of an aromatic dicarboxylic acid and a C<sub>2</sub>-C<sub>4</sub> diol,

5 the polyamide hard segments are polyamides of C<sub>6</sub> or higher, preferably C<sub>10</sub>-C<sub>12</sub>, carboxylic acids and C<sub>6</sub> or higher, preferably C<sub>10</sub>-C<sub>12</sub>, organic diamines or of C<sub>6</sub> or higher, preferably C<sub>10</sub>-C<sub>12</sub>, aliphatic ω-amino-α-acids, and

10 the polyether soft segments are polyethers of C<sub>2</sub>-C<sub>10</sub>, preferably C<sub>4</sub>-C<sub>6</sub> diols;

the block copolymer has a low flexural modulus, namely less than 150,000 psi, preferably less than 120,000 psi;

the block copolymer has a hardness, Shore D scale, of greater than 60; and

15 the percentage by weight of the block polymer attributable to the hard segments is between about 50% and about 95%.

From such polymers, balloons having compliant to semi-compliant expansion profiles can be prepared with wall strengths greater than 15,000 psi, frequently greater than 20,000 psi. The high strength of the balloons produced from the  
20 polymers allows for construction of low profile catheters and the low flexural modulus contributes to a softer feel found with the balloons of the invention, compared to those made of other high strength polymer materials. Low profile catheters made with the inventive balloons have very good initial crossing, good trackability and good recrossing after first inflation.

25


#### Description of the Drawings

Fig. 1 is a graph of the distension from nominal diameter to burst of several balloons of the invention prepared from a polyamide/polyether polyester block copolymer using different hoop ratios to form the balloon.

30 Fig. 2 is a graph as in Figure 1 using an alternate polyamide/polyether polyester block copolymer to form the balloon of the invention.

### Detailed Description of the Invention

The preferred balloons of the invention are made of polyamide/polyether block copolymers. The polyamide/polyether block copolymers are commonly identified by the acronym PEBA (polyether block amide). The polyamide and polyether segments of these block copolymers may be linked through amide linkages, however, most preferred are ester linked segmented polymers, *i.e.* polyamide/polyether polyesters. Such polyamide/polyether/polyester block copolymers are made by a molten state polycondensation reaction of a dicarboxylic polyamide and a polyether diol. The result is a short chain polyester made up of blocks of polyamide and polyether. The polyamide and polyether blocks are not miscible. Thus the materials are characterized by a two phase structure: one is a thermoplastic region that is primarily polyamide and the other is elastomer region that is rich in polyether. The polyamide segments are semicrystalline at room temperature. The generalized chemical formula for these polyester polymers may be represented by the following formula:



in which PA is a polyamide segment, PE is a polyether segment and the repeating number *n* is between 5 and 10.

The polyamide segments are suitably aliphatic polyamides, such as nylons 12, 11, 9, 6, 6/12, 6/11, 6/9, or 6/6. Most preferably they are nylon 12 segments. The polyamide segments may also be based on aromatic polyamides but in such case significantly lower compliance characteristics are to be expected. The polyamide segments are relatively low molecular weight, generally within the range of 500-8,000, more preferably 2,000-6,000, most preferably about 3,000-5,000.

The polyether segments are aliphatic polyethers having at least 2 and no more than 10 linear saturated aliphatic carbon atoms between ether linkages. More preferably the ether segments have 4-6 carbons between ether linkages, and most preferably they are poly(tetramethylene ether) segments. Examples of other polyethers

which may be employed in place of the preferred tetramethylene ether segments include polyethylene glycol, polypropylene glycol, poly(pentamethylene ether) and poly(hexamethylene ether). The hydrocarbon portions of the polyether may be optionally branched. An example is the polyether of 2-ethylhexane diol. Generally  
5 such branches will contain no more than two carbon atoms. The molecular weight of the polyether segments is suitably between about 400 and 2,500, preferably between 650 and 1000.

The weight ratio of polyamide to polyether in the polyamide/polyether polyesters used in the invention desirably should be in the range of 50/50 to 95/5,  
10 preferably between 60/30 and 92/08, more preferably, between 70/30 and 90/10.

Polyamide/polyether polyesters are sold commercially under the PEBAX trademark by Atochem North America, Inc., Philadelphia PA. Examples of suitable commercially available polymers are the Pebax® 33 series polymers with hardness 60 and above, Shore D scale, especially Pebax® 7033 and 6333. These polymers are  
15 made up of nylon 12 segments and poly(tetramethylene ether) segments in about 90/10 and about 80/20 weight ratios, respectively. The average molecular weight of the individual segments of nylon 12 is in the range of about 3,000-5,000 grams/mole and of the poly(tetramethylene ether) segments are in the ranges of about 750-1,250 for the 6333 polymer and about 500-800 for the 7033 polymer. The inherent viscosities of  
20 these polymers are in the range of 1.33 to 1.50 dl/g.

Generally speaking, balloons of Pebax® 7033 type polymer exhibit borderline non-compliant to semi-compliant behavior and balloons of Pebax® 6333 type polymer show semi-compliant to compliant distension behavior, depending on the balloon forming conditions.

25 While the Pebax ®-type polyamide/polyether polyesters are most preferred, it is also possible to use other PEBA polymers with the physical properties specified herein and obtain similar compliance, strength and softness characteristics in the finished balloon.

As an alternative to polyamide elastomers, it is also possible to utilize  
30 polyester/polyether segmented block copolymers and obtain similar balloon properties. Such polymers are made up of at least two polyester and at least two polyether segments. The polyether segments are the same as previously described for the

polyamide/polyether block copolymers useful in the invention. The polyester segments are polyesters of an aromatic dicarboxylic acid and a two to four carbon diol.

Suitable dicarboxylic acids used to prepare the polyester segments of the polyester/polyether block copolymers are ortho-, meta- or para- phthalic acid,  
5    naphthalenedicarboxylic acid or meta-terphenyl-4,4'-dicarboxylic acids.

Preferred polyester/polyether block copolymers are poly(butylene terephthalate)-*block*-poly(tetramethylene oxide) polymers such as Arnitel EM 740, sold by DSM Engineering Plastics. Hytrel polymers, sold by DuPont which meet the physical and chemical specifications set out herein can also be used, but are less  
10    preferred.

It is believed important that the block copolymers have a hardness, Shore D scale, of at least 60 and a flexural modulus of no more than about 150,000, in order to obtain the desirable combination of strength, compliance and softness characteristics which distinguish the inventive balloons. Preferably the Shore D hardness is in the  
15    range of 65-75 and the flexural modulus is in the range of 50,000-120,000. The preferred polymers useful in the invention are also characterized by a high ultimate elongation of about 300% or higher and an ultimate tensile strength of at least 6,000 psi.

The balloons of the invention are made using known techniques for forming catheter balloons. For coronary angioplasty catheter balloons (balloon  
20    diameters of about 1.5-4.0 mm), single wall thicknesses of less than 0.001 inches, preferably less than 0.0007 inches, are readily obtained. Wall strengths for such balloons are in excess of 15,000, typically at least 18,000 psi, and in most cases in the range of about 20,000 to 32,000 psi. For peripheral angioplasty, balloons of up to 10 mm diameter may be used and in such cases somewhat thicker walls may be employed.  
25    Even with a 10 mm balloon, wall thicknesses of about 0.0015 mm or less can be employed to provide balloons with burst pressures of at least 10 atm. Suitably the balloons are formed by expansion of tubing at a hoop ratio (mold diameter/tubing ID) of between 3 and 8, preferably between 4 and 7.

The following examples illustrate the preparation and unique properties  
30    of balloons of the invention.

## EXAMPLES

### TUBING EXTRUSION:

In examples 1-9, 11 and 13 all tubing materials were made from Atochem Pebax® 7033 and Pebax® 6333 by extrusion. Polymer pellets were dried to  
5 less than 0.10 wt% moisture content before extrusion. Tubing was extruded at melt temperature range of 200°C to 220°C by hot feedthroat through seven extruder zones with controlled temperatures. The extrusion conditions were based upon manufacturer's recommended polymer processing conditions. After the polymer material extruded out of the die in tube form it passed through a small air gap and was cooled in a deionized  
10 water bath maintained at about 65°F. A puller was used to pull the tube through the water bath. After passing through the puller, the extruded tubing was cut into 8 inch sections or spooled. A variety of tubing sizes were made by this method.

### EXAMPLE 1

The product of this example is a 2.25 mm balloon made from Pebax®  
15 7033. This polymer has a Shore D hardness of 69, a flexural modulus of 67,000, an ultimate tensile strength of 8,300 psi and an ultimate elongation of 400%. The tubing sections had an OD of 0.0270 inch and an ID of 0.0179 inch. In order to form a 2.25 mm balloon with a 20 mm body length, a mold having dimensions that allowed the tube to blow out to the appropriate body size and balloon waist inner diameters was used.

20 After the tubing section was securely inside the mold, the mold was placed in a holder. The tubing section extended out the top of the mold and was fed into a Touhy clamp through which nitrogen gas applied to the inner lumen of the tubing at 280 psi with tension applied to the tubing. The tubing section at the bottom of the mold was clamped off such that the pressure was maintained inside the tubing section. The  
25 mold was then gradually dipped into a deionized hot water bath maintained at 90°C ( $\pm 1^\circ\text{C}$ ) to a point just above the proximal waist portion of the mold at a controlled manner. A balloon was formed by radial expansion with internal pressure using a hoop ratio of 5.1. After the balloon formed, the mold was removed from the hot water bath and cooled for approximately 10 sec in a deionized water bath maintained at about  
30 10°C.

Balloons prepared in this manner were subjected to standard burst tests by measuring the double wall thickness of the deflated balloon, inflating the balloon at

incrementally increasing pressures and measuring the outside diameter at each increment until the balloon burst. Burst strength, distension and balloon wall strength were calculated from the data obtained. Average results are given in Table 1.

#### EXAMPLE 2

5           The product of this example is a 3.00 mm balloon made from Pebax® 7033. The tubing sections had an OD of 0.0290 inch and an ID of 0.0179 inch. A 3.00 mm size mold was used to produce the balloons. These 3.00 mm balloons were made by the same procedure used in example 1, except for the water bath temperature and internal blowing pressure. The water bath temperature and the pressure were  
10 maintained at 95°C and 300 psi, respectively. The hoop ratio of the balloon was 6.2. The results of testing for burst, distension and wall strength are also listed in Table 1.

#### EXAMPLE 3

          The product of this example is a 3.00 mm balloon made from Pebax® 7033. The tubing sections had an OD of 0.0316 inch and an ID of 0.0179 inch. A  
15 corresponding size mold was used to mold balloons. In this example, 90°C water bath and 400 psi internal blowing pressure were used. The test results provided in Table 1 show that these balloons gave a higher burst pressure than the previous examples.

#### EXAMPLE 4

          The product of this example is a 3.00 mm balloon made from Pebax®  
20 7033. The tubing sections had an OD of 0.0320 inch and an ID of 0.0215 inch. A 3.00 mm size mold was used to produce the balloons. The same molding conditions described in example 2 were used except that the tubing was prestretched at room temperature before molding balloons. The prestretch stretching ratio  $\lambda$  was 1.5 in this example. The test results of this example are listed in Table 1.

Table 1. Burst and Distension Test Results of Pebax® 7033 Material (averages of at least 5 balloons).

Example	Balloon Size (mm)	Single Wall Thickness (inch)	Burst Pressure (psi)	Distension 88 psi-Burst (%)	Distension 88 psi - 132 psi (%)	Distension 88 psi - 176 psi (%)	Wall Strength (psi)
1	2.25	0.00042	230	21.3	4.2	10.9	25400
2	3.00	0.00047	230	12.7	3.2	7.1	29200
3	3.00	0.00060	260	12.8	3.6	6.9	25900
4	3.00	0.00049	220	23.5	4.4	9.0	26300

#### EXAMPLE 5

Balloons having 2.0-3.0 mm diameters were prepared from Pebax® 7033 using hoop ratios of 4.6, 5.1 and 6.7. The balloons were expanded incrementally at 37°C until they burst. The results, plotted in Figure 1, show semi-compliant curves with very high burst strengths ranging from 15-18 atm and maximum distensions at burst of 24% - 45%.

#### EXAMPLE 6

In this example, balloons were made from Pebax® 6333. This polymer has a Shore D hardness of 63, a flexural modulus of 49,000, an ultimate tensile strength of 8,100 psi and an ultimate elongation of 300%. The same balloon forming procedure as in example 1 was used, except as noted below. The product of this example is a 2.5 mm balloon. The tubing sections had an OD of 0.0316 inch and an ID of 0.0179 inch. A 2.5 mm size mold was used to produce the balloons. In this example, a 95°C water bath and a 300 psi internal blowing pressure were used. The hoop ratio for blowing the balloon was 5.5. The results of burst, distension and wall strength are shown in Table 2.

#### EXAMPLE 7

Pebax® 6333 tubing with an OD of 0.0310 inch and an ID of 0.0170 inch was used to produce 3.0 mm balloon. The water bath temperature was 90°C and the internal blow pressure was 300 psi. The hoop ratio for blowing the balloon was 6.9. Test results are shown in Table 2.

**Table 2. Burst and Distension Test Results of Pebax® 6333 Material (averages of at least five balloons)**

Example	Balloon Size (mm)	Single Wall Thickness (inch)	Burst Pressure (psi)	Distension 88 psi-Burst (%)	Distension 88 psi - 132 psi (%)	Distension 88 psi - 176 psi (%)	Wall Strength (psi)
6	2.50	0.00058	220	33.7	3.4	17.4	19900
7	3.00	0.00049	210	17.1	4.2	9.7	26100

10

#### EXAMPLE 8

Balloons having 2.25-3.0 mm diameters were prepared from Pebax® 6333 using hoop ratios of 4.2, 5.5 and 6.9. The balloons were expanded incrementally at 37°C until they burst. The results, plotted in Figure 2, show semi-compliant and compliant curves with burst strengths of 11.5-14 atm and distensions at burst of 23% - 69%.

#### EXAMPLE 9

The products of this example were 3.00 mm balloons made from Pebax® 6333. The tubing sections had an OD of 0.0350 inch and an ID of 0.0190 inch. A 3.00 mm size mold was used to produce the balloons. Portions of the tubing sections were prestretched at a stretching ratio of 2 ( $\lambda=2$ ) before molding the balloons. The prestretched portions were on either side of a central 8 mm unstretched portion protected during the prestretching operation by a clamp. The unstretched central portion was then formed into a 20 mm long, 3.0 mm diameter balloon body by expansion under pressure in a mold as in the previous examples. The temperature of the water bath was 95°C and the expansion pressure was 340 psi. The balloons made in this manner had a hoop ratio of 6.2, a single body wall thickness of between 0.0006 and 0.0007 inches, a distal waist wall thickness of between 0.0014 and 0.0021 inches a proximal waist wall thickness of between 0.0014 and 0.0018 inches. The burst pressure of the balloons was about 270 psi. The balloon distension was semi-compliant.

30

#### EXAMPLE 10

The material used in this example was Arnitel EM 740 sold by DSM Engineering Plastics. This polymer had a Shore hardness of 74D, a flexural modulus 120,000 psi, an ultimate tensile strength of 6,400 psi and an ultimate elongation of

340%. 2.25 mm Balloons were prepared from tubing of dimensions OD = 0.0270 inches and ID = 0.0179 inches. The tubing was necked at two ends and the balloon body portion was unstretched, as described in Example 9. The molding temperature was 80°C. The molding pressure was 290 psi. The molding tension was 50 grams.

5 Balloon properties are given in Table 3.

**Table 3: Burst and Distention Test Results of Arnitel EM 740 Material**

Example	Balloon Size (mm)	Single Wall Thickness (inch)	Burst Pressure (psi)	Distention 88-Burst %	Distention 88-132 %	Distention 88-176 %	Wall Strength (psi)
10 11	2.25	0.00041	238	34	6.2	16.7	25,700

#### EXAMPLE 11

The material used in this example was Pebax 7033. The molding temperature was 95° C. The molding pressure was 500 psi. 2.00 mm Balloons were prepared from tubing segments as set forth below. All tubing segments were stretched at room temperature with different stretching ratios and starting tubing dimensions. The unit of ID and OD is inches.

- a: the tubing was stretched at  $\lambda = 2.5$  stretching ratio
- 20 starting ID = 0.0130, OD = 0.0252
- ending ID = 0.0087, OD = 0.0177
- b: the tubing was stretched a  $\lambda = 3.0$  stretching ratio
- starting ID = 0.0132, OD = 0.0252
- ending ID = 0.0081, OD = 0.0162
- 25 c: the tubing was stretched at  $\lambda = 4.5$  stretching ratio
- starting ID = 0.0132, OD = 0.0262
- ending ID = 0.0064, OD = 0.0136

The properties of the resulting balloons are set forth in Table 4.

Table 4: Burst and Distention Test Results of Pebax 7033 Material

Example	Balloon Size (mm)	Single Wall Thickness (inch)	Burst Pressure (psi)	Distention 88-Burst (%)	Distention 88-132 (%)	Distention 88-176 (%)	Wall Strength (psi)
12 a	2.0	0.00058	279	14.6	4.0	6.5	18,900
12 b	2.0	0.00060	279	14.6	3.5	6.6	18,300
12 c	2.0	0.00062	353	22.2	3.0	5.4	22,600

## EXAMPLE 12

The material used in this example was Arnitel EM 740 poly(butylene terephthalate-*block*-poly(tetramethylene oxide)). 2.75 mm Balloons were prepared from tubing of dimensions: OD = 0.0390 inches and ID = 0.0230 inches. The tubing was stretched at room temperature at  $\lambda = 4.8$ . The dimension of stretched tube was: OD = 0.0250 inches and ID = 0.0200 inches. The molding temperature was 80°C. The molding pressure was 490 psi. The molding tension was 30 grams. The properties of the resulting balloons are set forth in Table 5.

Table 5: Burst and Distention Test Results of Arnitel EM 740 Material

Example	Balloon Size (mm)	Single Wall Thickness (inch)	Burst Pressure (psi)	Distention 88-Burst %	Distention 88-132 %	Distention 88-176 %	Wall Strength (psi)
13	2.75	0.00066	265	43.9	8.0	18.2	21,700

## EXAMPLE 13

Pebax 7033 tubes with dimensions 0.0198 inch OD and 0.0339 inch ID is drawn at room temperature with a central region protected by an inserted hypo tube approximately 0.018 inch in diameter and 1.0 inch in length. The tube was drawn until an 8 mm central region remained undrawn. Ten sterilized balloons (3.0 mm in diameter and 20 mm in length) with an average double wall thickness 0.00142 inch are made by radially expanding the 8 mm central tubing portion at 95°C. The resulting burst pressure is 270-280 psi and the distention is 9% over the range 88-176 psi and 16% over the range 88-235 psi.

## COMPARATIVE EXAMPLES

## COMPARATIVE EXAMPLES A-C

The material used in this example was Pebax 3533. This polymer has a Shore D hardness of 35 and a flexural modulus of 2,800. Balloons were made by expanding tubes of ID = 0.0330 inch and OD = 0.0480 inch. The molding temperature was 66°C. The molding pressure was 80 psi. Distension and burst were run at room temperature (22°C). Balloon properties are set forth in Table 6.

**Table 6: Burst and Distention Test Results of Pebax 3533 Material**

Comparative Example	Balloon Size (mm)	Single Wall Thickness (inch)	Burst Pressure (psi)	Distention 10-Burst %	Wall Strength (psi)
A	1.50	0.00495	75	67	450
B	2.00	0.00218	50	89	900
C	2.50	0.00185	40	73	1060

#### COMPARATIVE EXAMPLE D

The material used in this example was Pebax 5533. This polymer has a Shore D hardness of 55 and a flexural modulus of 29,000. 3.00 mm balloons were prepared from tubing sections having an ID of 0.0190 inch and an OD of 0.0360 inch. The molding temperature was 87.5°C. The molding pressure was 300 psi. Portions of the tubing sections were prestretched at a stretching ratio of 2 ( $\lambda=2$ ) before molding the balloons. The prestretched portions were on either side of an 8 mm central unstretched portion protected during the prestretching operation by a hypo tube as in example 13. The unstretched central portion was then formed into a 20 mm long, 3.0 mm diameter balloon body by expansion under pressure in a mold. Balloon properties are set forth in Table 7.

**Table 7: Burst and Distention Test Results of Pebax 5533 Material**

Comparative Example	Balloon Size (mm)	Single Wall Thickness (inch)	Burst Pressure (psi)	Distention 88-burst %	Distention 88-132	Distention 29.4-Burst %	Wall Strength (psi)
D	3.00	0.00073	132	17.0	17.0	44.3	10,700

#### COMPARATIVE EXAMPLES E-G

The material used in this example was Riteflex 640 poly(butylene terephthalate-*block*-poly(tetramethylene oxide). This polymer has a Shore D hardness of 40 and a flexural modulus of 12,300. Balloons were made by expanding tubes of ID

= 0.0360 inch and OD = 0.0430 inch. The molding temperature was 80°C. The molding pressure was 80 psi. Balloon properties are set forth in Table 8.

**Table 8: Burst and Distention Test Results of Riteflex 640 Material**

Comparative Example	Balloon Size (mm)	Single Wall Thickness (inch)	Burst Pressure (psi)	Distention 10-Burst %	Wall Strength (psi)
E	1.50	0.00216	80	66	1100
F	1.75	0.00105	65	52	2100
G	2.25	0.00088	60	62	3020

## Claims

What is claimed is:

- 5 1. A balloon for a medical device formed from a length of polymer tubing by radial expansion of the tubing under pressure, the polymer being a block copolymer thermoplastic elastomer characterized as follows:
 

the block copolymer comprises two or more hard segments of a polyester or polyamide and two or more soft segments of polyether;

10 the polyester hard segments are polyesters of an aromatic dicarboxylic acid and a C<sub>2</sub>-C<sub>4</sub> diol,


the polyamide hard segments are polyamides of C<sub>6</sub> or higher carboxylic acids and C<sub>6</sub> or higher organic diamines or of C<sub>6</sub> or higher aliphatic ω-amino-α-acids, and

15 the polyether soft segments are polyethers of C<sub>2</sub>-C<sub>10</sub> diols,

the block copolymer has a flexural modulus of less than about 150,000 psi;

the block copolymer has a hardness, Shore D scale, of greater than 60; and

20 the percentage by weight of the block polymer attributable to the hard segments is between about 50% and about 95%.
2. A balloon as in claim 1 wherein the block copolymer has a Shore D hardness in the range of 65-75 and a flexural modulus in the range of 50,000-120,000 psi.
- 25 3. A balloon as in claim 1 wherein the hard segments of the block copolymer are polyamide segments.
4. A balloon as in claim 3 wherein the block copolymer is represented by the formula:




in which PA is a polyamide segment of molecular weight in the range of 500-8,000; PE is a polyether segment of molecular weight in the range of 500-2,500 and the repeating number n is between 5 and 10.

- 5 5. A balloon as in claim 4 wherein the block copolymer segment, PA, is an aliphatic polyamide of one or more C<sub>10</sub>-C<sub>12</sub> aliphatic acids and one or more C<sub>10</sub>-C<sub>12</sub> aliphatic diamines or of a C<sub>10</sub>-C<sub>12</sub> aliphatic  $\omega$ -amino - $\alpha$ - acid.
6. A balloon as in claim 4 wherein the polyamide segment, PA, is selected from the group consisting of nylon 12, nylon 11, nylon 9, nylon 6, nylon 6/12, nylon 6/11, nylon 6/9 and nylon 6/6.
- 10 7. A balloon as in claim 4 wherein the polyamide segment, PA, is nylon 12 of a molecular weight of 3,000-5,000, and the polyether segment, PE, is poly(tetramethylene ether) of molecular weight between 500 and 1250.
8. A balloon as in claim 4 wherein the polyamide segments, PA, comprise between 80 and 90% by weight of the polyamide/polyether polyester.
- 15 9. A balloon as in claim 1 wherein said polyether segment, is selected from the group consisting of poly(tetramethylene ether), poly(pentamethylene ether) and poly(hexamethylene ether).
10. A balloon as in claim 1 wherein the wall strength of the balloon is at least 15,000 psi.
- 20 11. A balloon as in claim 10 wherein the wall thickness, single wall basis, is no more than 0.0015 inches and said wall strength is greater than 18,000 psi.
12. A balloon as in claim 11 wherein said wall thickness is no more than 0.0009 inches.
13. A balloon as in claim 10 wherein said wall strength is greater than 20,000 psi.
- 25 14. A balloon as in claim 1 having a compliant to semi-compliant distension profile whereby as inflation pressure is increased from 6 atm to 12 atm, the balloon expands from a nominal diameter at the 6 atm pressure to an increased diameter at the 12 atm pressure which is at least 7% greater than said nominal diameter.
- 30 15. A balloon as in claim 14 wherein the increased diameter at 12 atm is at least 10% greater than said nominal diameter.


16. A balloon as in claim 14 wherein the increased diameter is at least 16% greater than said nominal diameter.
17. A balloon as in claim 14 having a nominal diameter of between 1.5 mm and 10.0 mm, the balloon having a burst pressure of at least 10 atm.
- 5 18. A balloon as in claim 1 having a nominal diameter of between 1.5 mm and 4.0 mm, the balloon having a burst pressure of at least 12 atm.
19. A balloon as in claim 1 wherein the hard segments of the block copolymer are polyester segments.
20. A balloon as in claim 19 wherein said polyester segments are polyesters
- 10 of an acid selected from the group consisting of ortho-, meta- or para- phthalic acid, naphthalenedicarboxylic acid and meta-terphenyl-4,4'-dicarboxylic acids and a diol selected from the group consisting of ethylene glycol, 1,3-propane diol and 1,4-butane diol.
21. A balloon as in claim 1 wherein the block copolymer is poly(butylene
- 15 terephthalate-*block*-poly(tetramethylene oxide).
22. A balloon as in claim 1 wherein the block copolymer is further characterized by a ultimate tensile strength of at least 6,000 psi and an ultimate elongation of at least 300%.
23. A dilation catheter having a elongated tubular body, a balloon mounted
- 20 on a distal end thereof and means for inflation of the balloon, wherein the balloon is a balloon as in claim 1.
24. A method of forming a balloon for a medical device, the balloon having proximal and distal waist portions and a central body portion, comprising radially expanding a length of polymer tubing under pressure, wherein said length of tubing has
- 25 proximal and distal portions which are stretched to a reduced diameter and an unstretched central portion, and said radially expanding step is accomplished by expanding said tubing in a mold such that the balloon body is formed from the unstretched central portion of the tubing and the proximal and distal waist portions of the balloon are formed from the stretched proximal and distal portions of the tubing, and
- 30 wherein the polymer is a block polyamide/polyether or a polyester/polyether copolymer.
25. A method as in claim 24 wherein the tubing is radially expanded at a hoop ratio of between 3 and 8.

26. A method as in claim 24 wherein the tubing is radially expanded at a hoop ratio of between 4 and 7.
27. A method as in claim 24 wherein the polymer has a Shore D hardness of at least 60 and a flexural modulus of less than 150,000 psi.
28. A method as in claim 27 wherein the polymer has an ultimate tensile strength of at least 6000 psi and an ultimate elongation of at least 300%.
29. A method as in claim 24 wherein the balloon is not heat set after said radially expanding step and the balloon obtained thereby has a wall strength of at least 20,000 psi.
30. A method as in claim 24 wherein said proximal and distal portion stretching step are performed at ambient temperature.
31. A method as in claim 21 wherein said polymer is a polyamide/polyether/polyester.

1/2

*Fig. 1*

2/2

**Fig. 2**

SUBSTITUTE SHEET (RULE 26)

## INTERNATIONAL SEARCH REPORT

 Intern: 1 Application No  
 PCT/US 95/02717

 A. CLASSIFICATION OF SUBJECT MATTER  
 IPC 6 A61L29/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 A61L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO,A,84 01513 (HARDCASTLE D.) 26 April 1984 see claims 1,4	1,3
Y	FR,A,2 651 681 (MEDICORP RESEARCH) 15 March 1991 see claims 1,5	1,3
A	EP,A,0 566 755 (CORDIS) 27 October 1993 see claims 1-3,9,19,22	1-9
A	EP,A,0 513 459 (TERUMO) 19 November 1992 see claims 1,4	1,9,19
P,A	EP,A,0 592 885 (BARD C.R.) 20 April 1994 cited in the application see claim 11	1

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

\*A\* document member of the same patent family

Date of the actual completion of the international search

29 June 1995

Date of mailing of the international search report

06.07.95.

Name and mailing address of the ISA

 European Patent Office, P.B. 5818 Patentlaan 2  
 NL - 2280 HV Rijswijk  
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
 Fax: (+31-70) 340-3016

Authorized officer

Peltre, C

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 95/02717

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-8401513	26-04-84	EP-A, B 0121533 US-A- 4820270	17-10-84 11-04-89
FR-A-2651681	15-03-91	NONE	
EP-A-566755	27-10-93	NONE	
EP-A-513459	19-11-92	NONE	
EP-A-592885	20-04-94	CA-A- 2107378 JP-A- 6304920	31-03-94 01-11-94